



TECHNICAL INFORMATION

WOOD STAIN – LASURE AQUA



DESCRIPTION:

Wood stain/lasure protector water of wood of high quality formulated with acrylic resins and UV solar filter for protection and decoration of wood.

Features:

-) Highlight the natural appearing of the wood.
-) Contains UV solar filter.
-) No peeling off.
-) Micro porous film.
-) Breathable to water vapour (inside the wood).
-) No cracking or flaking.
-) Fast drying.
-) Interior and exterior.

TECHNICAL DATA:

Fixed vehicle	Acrylics resins.	
Colour	Chart colours BARNIZ – LASUR.	
Gloss	Satin.	
Solids by weight	34 %	UNE-EN ISO 3251
Solids by volume	29 %	UNE 48090
Viscosity	80 – 90 KU (23 ± 2 °C)	UNE 48076
Specific weight	0.95 – 1.05 Kg./l (23 ± 2 °C)	UNE-EN ISO 2811-1
pH	> 8.0 (23 ± 2 °C)	UNE-EN ISO 787-9
Theoretical spreading rate	10 – 12 m ² /l and coat. Take in mind application leaking, surface irregularities, etc.	
Recommended thickness	80 – 100 microns wet; 24 – 30 microns dry per coat. Apply 2 coats as finish.	
Total drying	1 hour at 23 °C and 55% relative humidity. Depend on air temperature and ventilation.	UNE 48301
Repaint	8 – 12 hours.	
Solvent	Water.	

EU limit value for this product (cat. A/e): 130 g/l (2010). Max. content VOC: 40 g/l

APLICACION:

Decoration and protection of wood exposed to the weather. Penetrates wood, highlighting its natural veining.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5

Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

WOOD STAIN – LASURE AQUA



INSTRUCTIONS FOR USE:

Application methods: brush or spray.
Thinner and cleaning utensils: Water.

Painted surfaces must be dry and clean of dust, rust, grease, etc.

The number of coats to apply of tinted WOOD STAIN - LASURE AQUA will affect the obtained final colour.

The wood highly resinous must be cleaned previously with SYNTETIC AND GREASE SOLVENT, UNIVERSAL SOLVENT or ODOURLESS SOLVENT, to avoid problems during the drying.

) Unpainted surfaces:

- Standard wood: Apply the product diluted 5% with water, to obtain a perfect finishing is recommended to apply 3 coats waiting and sanding between application around 8 – 12 hours.

) Painted surfaces:

- Remove paint and varnish by polishing or sanding until complete elimination. After that proceed as non painted surfaces

In general we recommend:

-) Apply between 5 °C and 35 °C.
-) It is not recommended to apply in full sun or high temperatures of the surface.
-) Perfectly mix the product before use.

PRESENTATION:

Plastic packaging of: 0.750 Litres; 4 Litres

STORAGE:

12 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

ADDITIONAL INFORMATION:

The information contained in this document serves as a guide for the user but does not constitute a guarantee. For information about safety and the environment, please refer to the Safety Data Sheet.